


## Moso<sup>®</sup> Solid Joist

### Product

The MOSO solid joist consists of 3 layers of bamboo (side pressed style). The joist has numerous applications, but is mostly applied as raw material for banisters (for which the material is being round milled).



*Solid joist side pressed*

### Product line

Code Natural	Code Caramel	Style	Thickness (mm)	Type	Construction (mm)	Dimensions (mm)
BL-200	BL-250	SP	55	3 ply	3x18,3	2440x55

SP = Side pressed

### Technical characteristics

- Hardness: 4,0 kg/mm<sup>2</sup> (Brinell)
- Shrink/swell: 0,14% per 1% change in moisture content
- Equilibrium MC: 10% at 20 °C and 65% Rel. Air Humidity  
8% at 20 °C and 50% Rel. Air Humidity
- Density: 700 kg/ m<sup>3</sup>
- Glue: D3 water resistant
- Fire resistance: EN 13501-1: Cfl-s1
- Emission formaldehyde: <0,124 mg/m<sup>3</sup> (E1 norm)